

S3110 / S3140 / S3170

SANDING SURFACER PLUS WHITE / GREY / BLACK

SYROXTM

DESCRIPTION

With its high solids content and great sanding properties, the Syrox Surfacers Plus have been formulated for use before Syrox Basecoat. It comes in three colours White S3110, Grey S3140 and Black S3170 which can be mixed to any shade for optimal Basecoat performance. When used with Syrox S3080 Non-Sanding Converter, Syrox Surfacers Plus can be used as non-sanding surfacer. By adding Syrox Surfacers Additive Fast S7300 air-drying times can be shortened for spot and part-panel repairs only.

SYROX REFINISH SYSTEM



PRODUCT LIST

- S3110 SANDING SURFACER PLUS WHITE
- S3140 SANDING SURFACER PLUS GREY
- S3170 SANDING SURFACER PLUS BLACK
- S6000 HS ACTIVATOR SLOW
- S6010 HS ACTIVATOR STANDARD
- S6020 HS ACTIVATOR FAST
- S6030 HS ACTIVATOR VERY FAST
- S3080 NON SANDING CONVERTER
- S7300 SURFACER ADDITIVE FAST
- S8000 THINNER

FEATURES

- Available in three colours White / Grey / Black
- 5 designated shades for improved basecoat performance
- Convertible to a non-sanding version
- Easy mixing ratios & excellent topcoat hold out
- Fast drying times for spot repairs



TECHNICAL DATA SHEET

S3110 / S3140 / S3170


SANDING SURFACER PLUS WHITE / GREY / BLACK



Product preparation - application STANDARD SANDING



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Steel, galvanized steel or soft aluminium, sanded and cleaned and coated with S2000 1K Wash Primer.

Old or original paintwork well sanded and cleaned.

OEM Primer (e-coat), sanded and cleaned.

Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.

Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



	Very fast		Fast		Standard		Slow	
	Volume	Weight	Volume	Weight	Volume	Weight	Volume	Weight
S31X0	5	100	5	100	5	100	5	100
S6000	-	-	-	-	-	-	1	14
S6010	-	-	-	-	1	14	-	-
S6020	-	-	1	14	-	-	-	-
S6030	1	14	-	-	-	-	-	-
S8000	0 - 15 %	0 - 10	0 - 15 %	0 - 10	0 - 15 %	0 - 10	0 - 15 %	0 - 10



Pot life at 20°C: 45 min - 1 hr 30 min



	Spray nozzle	Spray pressure	
Compliant	1.6 - 1.9	1.5 - 2 bar	inlet pressure
HVLP	1.6 - 1.9	0.7 bar	atomisation pressure

see manufacturer's instructions



1 - 3 coats

with intermediate and final flash-off until flat



S6000 / S6010 / S6020 / S6030	
20 °C	4 hr
60 - 65 °C	20 min - 30 min



P360 - P500
P800 - P1000



Syrox Waterborne Basecoat + Syrox Clearcoats

VOC compliant

2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

TECHNICAL DATA SHEET

S3110 / S3140 / S3170


SANDING SURFACER PLUS WHITE / GREY / BLACK



Product preparation - application STANDARD SANDING ACCELERATED



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Steel, galvanized steel or soft aluminium, sanded and cleaned and coated with S2000 1K Wash Primer.

Old or original paintwork well sanded and cleaned.

OEM Primer (e-coat), sanded and cleaned.

Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.

Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



Spot and panel repair		
	Volume	Weight
S31X0	5	100
S6020 / S6030 *	1	14
S7300	10 - 15 %	7 - 11

* Potlife: Use immediately



Pot life at 20°C: 10 min



	Spray nozzle	Spray pressure	
Compliant	1.6 - 1.9	1.5 - 2 bar	inlet pressure
HVLP	1.6 - 1.9	0.7 bar	atomisation pressure

see manufacturer's instructions



1 - 3 coats

with intermediate and final flash-off until flat



S6020 / S6030	
20 °C	2 hr - 3 hr



P360 - P500
P800 - P1000



Syrox Waterborne Basecoat + Syrox Clearcoats

VOC compliant

2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

TECHNICAL DATA SHEET

S3110 / S3140 / S3170


SANDING SURFACER PLUS WHITE / GREY / BLACK



Product preparation - application STANDARD NON-SANDING



It is strongly recommended to use appropriate personal protection equipment during application to avoid respiratory, skin and eye irritation.



Steel, galvanized steel or soft aluminium, sanded and cleaned and coated with S2000 1K Wash Primer.

Old or original paintwork well sanded and cleaned.

OEM Primer (e-coat), sanded and cleaned.

Surfaces pretreated with 2K polyester products and then finely sanded and cleaned.

Glass fibre reinforced polyester substrates, free of release agents, sanded and cleaned.



	Standard		Slow	
	Volume	Weight	Volume	Weight
S31X0	3	100	3	100
S6000	-	-	1	23
S6010 / S6020	1	23	-	-
S3080	45 %	37	45 %	37



Pot life at 20°C: 1 hr



	Spray nozzle	Spray pressure	
Compliant	1.3 - 1.4	1.8 - 2 bar	inlet pressure
HVLP	1.3 - 1.4	0.7 bar	atomisation pressure

see manufacturer's instructions



1 coat

final flash-off: 30 min - 8 hr Syrox Basecoat: 30 min - 8hrs.



Syrox Waterborne Basecoat + Syrox Clearcoats

VOC compliant

2004/42/IIB(c)(540) 540: The EU limit value for this product (product category: IIB(c)) in ready to use form is maximum 540 g/l of VOC. The VOC content of this product in ready to use form is maximum 540 g/l.

TECHNICAL DATA SHEET

S3110 / S3140 / S3170

SANDING SURFACER PLUS WHITE / GREY / BLACK




Products

S3110 SANDING SURFACER PLUS WHITE
S3140 SANDING SURFACER PLUS GREY
S3170 SANDING SURFACER PLUS BLACK


S6000 HS ACTIVATOR SLOW
S6010 HS ACTIVATOR STANDARD
S6020 HS ACTIVATOR FAST
S6030 HS ACTIVATOR VERY FAST

S3080 NON SANDING CONVERTER
S7300 SURFACER ADDITIVE FAST
S8000 THINNER

Product mix



Mixing ratios with special agents are available in the productmix table on Colour Search and in the specific TDS.



60 - 80 µm per coat (sanding surfacer)
20 - 30 µm non-sanding

Theoretical coverage

380 - 460 m²/l at 1 micron dry film thickness
Due to different Activator characteristics and different mixing ratios of the ready-to-use mixture in some TDS versions, the theoretical coverage calculation may vary.
Note: The practical material consumption depends on several factors, e.g. geometry of the object, surface formation, application method, spray gun setting, inlet pressure, etc.



Clean after use with a suitable solventbased guncleaner.

Remarks

- Material has to be at room temperature (18-25°C) before use.
- Mix thoroughly and put can on mixing machine.
- Allow additional time for preheating up to panel temperature.
- When isolating certain spots - even on problem substrates - the best results are achieved with a medium film thickness of 80-120µm in 2 coats, after either air drying overnight or force drying/IR drying. With problem substrates, careful pretreatment is necessary and the Surfacers must be applied to the entire area.
- For dry film thicknesses of more than 150 micron air dry overnight at 20°C or 40 minutes at 60-65°C.
- Surplus ready for use material should not be returned to original can.
- Elastification:
Add 10 % S7000 Flexible Additive to S31x0, then mix 4:1 with HS Activator and 10-15% S8000.

TECHNICAL DATA SHEET

S3110 / S3140 / S3170

SANDING SURFACER PLUS WHITE / GREY / BLACK



	White	Light Grey	Grey	Dark Grey	Black
S3110	100	72.5	-	-	-
S3140	-	27.5	100	60	-
S3170	-	-	-	40	100

Consult Safety Data Sheet prior to use. Observe the precautionary notices displayed on the container.

All other products referred to in the refinish build up are from our Syrox product range. System properties will not be valid when the related material is used in combination with any other materials or additives which are not part of our Syrox product range, unless explicitly indicated otherwise.

For professional use only! The information provided in this documentation has been carefully selected and arranged by us. It is based upon our best knowledge on the subject at the date of issuance. The Information is given for information purposes only. We are not liable for its correctness, accuracy and completeness. It is up to the user to check the information with regard to up-to-dateness and suitability for his intended purpose. The intellectual property in this Information, including patents, trademarks and copyrights, is protected. All rights reserved. The relevant Material Safety Data Sheet and Warnings displayed on the product label need to be observed. We may modify and/ or discontinue operation of all or portions of this Information at any time in our sole discretion, without notice and assume no responsibility to update the Information. All rules set forth in this clause shall apply accordingly for any future changes and amendments.